



1527 White

1527 White, also called 1527SWT is a white, UL certificated, one component RTV silicone with super resistance to weathering and ultra violet(UV). This material has very good adhesion without the need for primers to a wide range of substrates. It can be used for a variety of interior and exterior bonding and sealing applications. 1527 White is formulated to perform at temperatures ranging from -54°C to 210°C.

Technology / Base	Poly(dimethyl) Siloxane
Type of Product	Silicone Sealant
Components	One Part
Curing	Moisture Cure
Appearance / Color	White
Consistency	Thixotropic Paste

Features and Benefits

- Excellent heat resistance properties
- Super resistance to ultra violet(UV) and weather
- Neutral cure low/no odor
- UL Certified
- Wide operating temperature range
- Easy to use for reworkable applications

Technical Data

Physical Property	Value	Condition/Method
Rheology		
Viscosity	Thixotropic Paste	
Density		
Specific Gravity	1.37	
Uncured Material Characteristics		
Tack Free Time	6 min	
Full Cure Time	24 hr ≥ 2mm	23±2°C and 50±5%RH
Cured Material Performance		
Thermal Service Range	-54 to 210°C	
Hardness	48 Shore A	ISO7619, GB/T531
Tensile Strength	2.3 MPa	ISO37, GB/528
Elongation to Break	300%	ISO37, GB/528
Lap Joint Shear Strength		
Aluminum	1.8 MPa	ISO4587, GB7124
Electrical Properties		
Volume Resistivity	1.0 x 10 ¹⁵ Ωcm	IEC60093, GB/T1692
Breakdown Voltage	20 kV/mm	IEC 60243-1, GB/T1695
Damp Heat Aging Testing		
Elongation at Break	320%	85°C, 85% RH for 1000 hr ISO37, GB/528
Tensile Strength	1.6 MPa	ISO37, GB/528

Test Sample Conditions: 2mm Thickness, Cured at 23±2°C, 50±5%RH for 7 days. Tested at 23±2°C



Typical Applications

- Internal and external bonding and sealing
- Appliance applications
- Lighting systems
- Battery sealing
- Sealing the side frames of solar cell.
- Sealing/adhesive the junction boxes of solar cell.
- Sealing the solar energy lamps.

Curing Conditions

Cure speed will vary with temperature, relative humidity, depth of material and presence of moisture. Some applications may require special surface preparation. At 23±2°C, 50±5% relative humidity, typical cure depth is 2mm in 24 hours. Requires more time to cure in colder or lower humidity conditions. Contact H.B. Fuller Company technical support for additional curing recommendations.

Storage and Shelf Life

Product shall be ideally store in a cool, dry area in unopened containers. 1527 has a shelf life of 12 months from the date of manufacture. Material should be stored at a temperature of 8-25°C. Do not return unused material back into the container.

General Instructions

- For best performance bond surfaces should be clean, dry and free of any contaminants and oils.
- Apply a continuous and even bead of silicone to one surface.
- Assemble parts immediately. Remove excess material at once.

Note

The values noted in this data sheet are typical properties only and are not intended to be used as material specifications. For assistance in writing a material specification, please contact H.B. Fuller Company for further details.

Ordering Information

Stock No.
152764, 400ml; 152763, 600ml;
15276602, 25kg; 15276903, 270kg

Safety and Disposal

For complete safety and handling information, please refer to the appropriate Safety Data Sheets prior to using this product.

H.B. Fuller Company,
Beijing Tonsan Adhesive Co., LTD.
5 Shuangyuan Rd.
Badachu High-Tech Zone
100041, Beijing, China

Date Modified: 01 March 2018

www.hbfuller.com

www.hbfullerengineering.com

Connecting what matters.™

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.



NOTE TO USER: by ordering/receiving product, you accept the H.B. Fuller General Terms and Conditions of Sale applicable in the region. Please request a copy if you have not received this documentation. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, (1) the total aggregate liability of H.B. Fuller for any claim or series of related claims, however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability, or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. (2) H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill, or any indirect or consequential losses arising out of or in connection with product supply. (3) Nothing in any term shall operate to exclude or limit H.B. Fuller's liability for fraud, gross negligence, death, or personal injury caused by negligence, or for breach of any mandatory implied terms unless permitted by law.

H.B. Fuller
www.hbfuller.com

©H.B. Fuller Company, 2021